



## TECHNICAL DATA SHEET CUTBACK MC 3000

**DESCRIPTION:**

Cutback Medium curing 3000 is a standard of ASTM D 2027-13, typically used a Prime cote suitable for road construction and to produce cutback with superior properties in road and waterproofing in retain walls and generally in light – to – moderate environment. This grade of cutback produced by the fully automated process runs continuously resulting in a constant and homogenous finished products quality.

**PACKAGING:**

Cutback Bituminous material is commonly packed 195 kg New steel Drums on pallet to prevent any leak of container also Bulk in bitumen Tanker.

**CHARACTERISTICS AND SPECIFICATIONS:**

Cut back is bitumen dissolved in a petroleum solvent such as gasoline or kerosene. The type of solvent controls the curing time whereas the amount controls the viscosity of the final product. Solvent is added to bitumen to decrease the viscosity of bitumen and allow the material to penetrate surfaces more effectively. This solvent will slowly evaporate and leave a final product that is similar in hardness to the original bitumen. The cutback asphalt MC-3000 applying to waterproofing of surfaces plug capillary voids, coat, and bond loose mineral particles. Wataniya Cutback is produced in compliance and conformity to International Standards such as AASHTO M 82 & ASTM D 2027-13, also meets the following specification requirements.

SPECIFICATIONS	UNIT	STANDARD	MIN	MAX
Kinematic viscosity at 60°C	cSt	ASTM D-2170	3000	6000
Flashpoint (tag open cup)	OC	ASTM D-3143	66	--
<b>DISTILLATION TEST</b>				
<b>DISTILLATE, VOLUME BY PERCENTAGE OF TOTAL DISTILLATE TO 680°F (360°C)</b>				
To 437°F (225°C)	%	ASTM D - 402	--	--
To 500°F (260°C)	--		--	15
To 600°F (316°C)	--		15	75
Residue from distillation to 680°F, (360°C) Percent volume by	%		80	--
<b>TEST ON RESIDUE FROM DISTILLATION TEST</b>				
Viscosity at 140°F(60°C)	Pa.S	ASTM D-2170	30	120
Penetration 77°F (25°C) 100g,5s	dmm	ASTM-D5	120	250
Ductility 77°F (25°C)	cm	ASTM-D113	100	--
Solubility in trichloroethylene	%	ASTM-2042	99	--
Water, percent volume	%	ASTM-D95	--	0.2

**Address:**

Head Office : Wataniya Group Building, Salim Street, Sulaymaniyah - Iraq  
 Baghdad Office : Zaitun Street, Harthiya Quarter, Baghdad - Iraq  
 Dubai Office : DMCC Business Center, Level No. 01, Unit No. 2631, Dubai - U.A.E.

**Tel No.**

+964 781 496 0222

**Email**

[info@wataniyagroup.com](mailto:info@wataniyagroup.com)

**Website:**

[www.wataniyagroup.com](http://www.wataniyagroup.com)